

**NAIL REINFORCING AGENT**

**Publication Number:** 56-123909 (JP 56123909 A) , September 29, 1981

**Inventors:**

- ISODA TOMIO

**Applicants**

- ISEHAN KK (A Japanese Company or Corporation), JP (Japan)

**Application Number:** 55-027364 (JP 8027364) , March 06, 1980

**International Class (IPC Edition 3):**

- A61K-007/04  
 A45D-031/00

**JAPIO Class:**

- 14.4 (ORGANIC CHEMISTRY--- Medicine)  
 14.2 (ORGANIC CHEMISTRY--- High Polymer Molecular Compounds)  
 30.3 (MISCELLANEOUS GOODS--- Clothing & Personal Belongings)

**Abstract:**

**PURPOSE:** To prepare a nail reinforcing agent giving tough coating film to reinforce the soft nail, and useful for the mending and prevention of cracks of flaky peeling of the nail, by mixing and dispersing short fibers of rayon, nylon, cotton, wool, etc. in a lacquer base.

**CONSTITUTION:** The nail reinforcing agent is obtained by dispersing fibers of rayon, nylon, polyester, cotton, wool, flax, silk, etc. of 0.5-15 denier in thickness and 0.5-3.0mm in length, homogeneously, in a colorless, white, or colored lacquer base. The nail reinforcing agent can be applied and dried in the same manner as conventional nail enamel, and cured to obtain a tough film dispersed with the short fibers. The combined effect of the fiber and the resin gives the coating film with extremely high toughness, and enables the reinforcement of the soft nail and the mending and prevention of the cracks and flaky peeling of the nail. Especially, the agent is effective to the crack of the nail by the bridging effect of the fibers at the crack. The amount of the fibers is 0.1-3% based on the whole composition. (From: Patent Abstracts of Japan, Section: C, Section No. 85, Vol. 05, No. 204, Pg. 17, December 24, 1981 )

JAPIO

© 2004 Japan Patent Information Organization. All rights reserved.  
Dialog® File Number 347 Accession Number 803609

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: 56123909 A

(43) Date of publication of application: 29 . 09 . 81

(51) Int. Cl

A61K 7/04

A45D 31/00

(21) Application number: 55027364

(71) Applicant: ISEHAN:KK

(22) Date of filing: 06 . 03 . 80

(72) Inventor: ISODA TOMIO

(54) NAIL REINFORCING AGENT

(57) Abstract:

PURPOSE: To prepare a nail reinforcing agent giving tough coating film to reinforce the soft nail, and useful for the mending and prevention of cracks or flaky peeling of the nail, by mixing and dispersing short fibers of rayon, nylon, cotton, wool, etc. in a lacquer base.

CONSTITUTION: The nail reinforcing agent is obtained by dispersing fibers of rayon, nylon, polyester, cotton, wool, flax, silk, etc. of 0.5W15 denier in thickness and 0.5W3.0mm in length, homogeneously, in a colorless, white, or colored lacquer base. The nail reinforcing

agent can be applied and dried in the same manner as conventional nail enamel, and cured to obtain a tough film dispersed with the short fibers. The combined effect of the fiber and the resin gives the coating film with extremely high toughness, and enables the reinforcement of the soft nail and the mending and prevention of the cracks and flaky peeling of the nail. Especially, the agent is effective to the crack of the nail by the bridging effect of the fibers at the crack. The amount of the fibers is 0.1W3% based on the whole composition.

COPYRIGHT: (C)1981,JPO&Japio

⑨ 日本国特許庁 (JP)  
 ⑩ 公開特許公報 (A)

⑪ 特許出願公開  
 昭56—123909

⑫ Int. Cl.<sup>3</sup>  
 A 61 K 7/04  
 A 45 D 31/00

識別記号

厅内整理番号  
 7432—4C  
 7001—3B

⑬ 公開 昭和56年(1981)9月29日  
 発明の数 1  
 著査請求 有

(全 2 頁)

④ 爪補強剤

⑤ 特 願 昭55—27364  
 ⑥ 出 願 昭55(1980)3月6日  
 ⑦ 発明者 磐田富美穂

横浜市神奈川区三ツ沢中町19—  
 25

⑧ 出願人 株式会社伊勢半  
 東京都千代田区五番町7番地

明細書

1. 発明の名称  
 爪補強剤

2. 特許請求の範囲

黒色または白色または有色のラッカーベースに対して、レーヨン、ナイロン、ポリエスチル、木綿、羊毛、麻、綿等の太さ0.5～15デニール、長さ0.5～3.0mmの黒色または有色の綿糸を均一に分散させたもので、爪に塗布することにより、軟らかい爪の強化、爪の割れや片状のはがれの修復および逆行防止等に効果的、さらにそのままネイルエナメルとしてあるいはベースコートとしても使用できる爪補強剤。

3. 発明の詳細な説明

本発明は爪の補強剤に関するものである。従来欠けたり、割れたり、また亂片状にはがれたりする爪を修理保護し、日常生活に対する不便を解消したり、ネイルエナメルをぬりやすくしたりする為に、いくつかの爪補強剤が販売された。

この多くは漆剝剤で、従来大別して二種類の原理でその効果を得ていた。

そのひとつは软らかい漆剝を小にしみ込ませて化学的に爪を強化するものであり、いまひとつはラッカーベースで、その表面の効果によって爪の割れた部分を接着したり、爪のみかけの強度を増したりするものである。しかしこれらにはいずれも欠点がある。前者はあまり効果が無いか、または効果があつても薬品による爪あるいは皮膚などの身体への害が心配されることが欠点

となり、また後者では実際上充分な強度はなかなか得られない。

そしてこれらの問題はいずれもその本質にもとづくものであり、それを解決することは困難である。

そこで本発明者は上記の欠点を持たない爪補強用塗布剤として通常のネイルエナメルあるいはベースコートに類似したラッカーベースに短かい綿糸を混入分散させたものを発明した。この補強剤は通常のネイルエナメルと同様に塗布、乾燥させることにより、短かい綿糸を分散させまま硬化し、綿糸と樹脂との複合効果により、きわめて丈夫な被膜となつて効果をあらわす。

处方例 (1)

レーヨン綿糸 (3 デニール、長さ 2 mm)	1.5 重量%
ニトロセルロース	14.0 重量%
アクリル樹脂	6.0 重量%
アルキッド樹脂	6.0 重量%
カンフル	5.0 重量%
酢酸フタル	25.0 重量%
酢酸エチル	10.0 重量%
トルエン	32.3 重量%
硬化チタン	0.2 重量%
合計	100.0 重量%

この例は通常の白色ネイルエナメルにレーヨンの短かい綿糸を加えたものに相当し、ベースコートあるいは単に補強剤として使用できる。これを塗布すると、綿糸と樹脂との複合効果によって軟らかい爪を見かけ

け上強くし、また爪が割れている場合はその割れ部分に縫合される縫線によってその割れが修復され、また割れがさらに進行する事を防止する。

これは従来の縫合の入っていないラッカータイプのものが割れの修復や進行防止にはほとんど効果がなかつたのと比較して著しい進歩である。また、これは次のような方法によつて使用すると先端から鱗片状にはがれかかつた爪の固定にも有効である。

a. まず通常のネイルエナメルと両端に爪上にハケで塗布し、次に爪の先端のはがれかかつている部分に塗布する。

b. 上記のものが半乾いた時に再度通常のネイルエナメルと両端にハケで塗布する。この時ハケの操作により爪の先端部分からは縫を少しほみ出させ、全体が半乾きになるまで待つて、この縫を指で内側におりまげ、鱗片状になつた部分にからめて固定する。

c. 最後に爪先部分を含む爪全体に塗布して仕上げる。これはこのままでも良いし、この上に通常のネイルエナメル等を塗布して仕上げても良い。

#### 処方例 (2)

ナイロン繊維(0.5 デニール、長さ1 mm、赤色)	1.0重量%
ニトロセルロース	15.0重量%
アルキッド樹脂	13.0重量%
カンフル	3.0重量%
フタル酸シブチル	3.0重量%
フチルアルコール	2.0重量%

0.5 ~ 3 mm が、塗布のしやすさ、接着効率の面からみて適当である。

酢酸アツル	20.0重量%
酢酸エチル	6.0重量%
トルエン	31.4重量%
ペントナイト	1.0重量%
ビニルチタン	2.0重量%
赤色202号	0.4重量%
赤色204号	0.2重量%
合 计	100.0重量%

これは従来の顔料入りのネイルエナメルにナイロンの繊維を分散させた型式のものである。これは従来のネイルエナメルとまったく同様に使用することが出来、細くて赤色の繊維を用いているために乾燥後も繊維があり目立たないので、通常のネイルエナメルによる上塗りは物に必要としない。またこれも処方例 (1)において示したのと同様な特長をもつ、すなはち、歯らしい爪を補強し、割れや、鱗片状のはがれの修復および進行防止をする。

これらの例の他にも繊維としてはポリエスチル等の合成繊維だけでなく木綿、羊毛、麻、綿等の天然繊維も使用可能である。この繊維の全體に対する配合は通常1%前後が適当であるが、最適の割合は繊維の性質、大きさ、長さ等によつて異なり、普通およそ0.1%から3%のあいだにある。一般的傾向として、繊維の配合量が少ないとその補強剤としての効果が少く、また多すぎるとみかけの粘度が上昇して塗布しにくくなってしまう。また繊維の太さは0.5 ~ 15 デニール、長さは



## PATENT ABSTRACTS OF JAPAN

(11) Publication number: 56123909 A

(43) Date of publication of application: 29.09.81

(51) Int. Cl.

**A61K 7/04****A45D 31/00**

(21) Application number: 55027364

(71) Applicant: ISEHAN:KK

(22) Date of filing: 06.03.80

(72) Inventor: ISODA TOMIO

**(54) NAIL REINFORCING AGENT****(57) Abstract:**

**PURPOSE:** To prepare a nail reinforcing agent giving tough coating film to reinforce the soft nail, and useful for the mending and prevention of cracks of flaky peeling of the nail, by mixing and dispersing short fibers of rayon, nylon, cotton, wool, etc. in a lacquer base.

**CONSTITUTION:** The nail reinforcing agent is obtained by dispersing fibers of rayon, nylon, polyester, cotton, wool, flax, silk, etc. of 0.5W15 denier in thickness and 0.5W3.0mm in length, homogeneously, in a colorless, white, or colored lacquer base. The nail reinforcing

agent can be applied and dried in the same manner as conventional nail enamel, and cured to obtain a tough film dispersed with the short fibers. The combined effect of the fiber and the resin gives the coating film with extremely high toughness, and enables the reinforcement of the soft nail and the mending and prevention of the cracks and flaky peeling of the nail. Especially, the agent is effective to the crack of the nail by the bridging effect of the fibers at the crack. The amount of the fibers is 0.1W3% based on the whole composition.

COPYRIGHT: (C)1981,JPO&amp;Japio